



product description

Therm 1 is a red, transparent, low-viscosity, liquid stereolithography resin that produces molded parts with excellent

High temperature resistance, the use temperature of the molded part is 150 °C without load, especially suitable for making high-resolution, strong and tough models, suitable for

It is suitable for industries that have high temperature resistance requirements such as baking paint, electroplating, and rapid mold.

main advantage

- Excellent high temperature performance
- Excellent dimensional stability
- High resolution and fine performance
- High strength & sturdiness



Therm 1 technical data

fluid properties	
Exterior	transparent red liquid
Viscosity	~268cps @ 30oC
density	~1.10 g/cm3 @ 25oC

Optical properties	
E _c	6.5 mJ/cm2 [critical exposure]
D _p	0.11 mm [transmission depth]
E ₁₀	68.8 mJ/cm2 [Irradiance yields 0.254 mm (0.01 inch) thickness]

Mechanical behavior		
Measurement methods	Performance description	Typical value
D638	Tensile Strength	42.7MPa
D638	Tensile modulus	3235MPa
D638	Elongation at break	1.5%
D790	Bending strength	96.6MPa
D790	Flexural modulus	3165MPa
D2240	Shore hardness	83D

Thermodynamic properties		
Measurement methods	Performance description	(UV+thermal) curing
D648	HDT @ 0.455MPa	101.9oC _
D648	HDT @ 1.82MPa	85.5oC _

Operating temperature	
Molding temperature	150ÿ (no load)

These typical values may vary according to different processing or post-processing procedures.

UnionTech 联泰

上海联泰科技股份有限公司
Shanghai Union Technology Corporation

Address: Room 102, Building 40, No. 258, Xinzhusan Road, Songjiang High-tech Park, Cachaing Development Zone, Shanghai (201612)

Tel: 400-138-8966, 021-6497 8786 Fax: 021-64978786*5180

Email: enquiry@uniontech3d.cn

Website: www.uniontech3d.cn

Dongguan Southern Office, China

Dongguan, No. 1 Gudian Road, Nanchang District, Dongguan City, Guangdong Province

Unit 01-03-04-05, Floor 03, Building F4, Tianan Cyber City

Tianjin Tianjin Office, China

No. 42, Hongli South Road, Nankai District, Tianjin

330, Block 8, Heanxing Science and Technology Park

China Jinjiang Fujian Office

Jinjiang International, Hongshan Road, Qingyang Street, Jinjiang

2nd Floor, Building 3, Industrial Design Park